

PRODUCT DATA SHEET



**FERROMOLYBDENUM
60/70**

DESCRIPTION

Ferromolybdenum can be used in any melting process to add molybdenum to all types of iron and steel, and is supplied in a range of sizes for furnace or ladle addition.

SPECIFICATIONS

Percent by Weight

Molybdenum (Mo)	60.00 – 70.00
Silicon (Si) (Soluble)	1.50 max
Copper (Cu)	0.50 max
Sulfur (S)	0.10 max
Carbon (C)	0.05 max
Phosphorus (P)	0.05 max
Balance	Principally Iron

STANDARD SIZES

1 – 5 mm
0 – 2 mm

PACKAGING

Steel drum	250 kg net
Bag	1000 kg net 2000 kg net

Produced by Climax Molybdenum U.K. Ltd., Stowmarket, Suffolk, United Kingdom.

SDS REQUIREMENTS

A copy of the safety data sheet (SDS) is available upon request.

QUALITY ASSURANCE / QUALITY CONTROL

All sites are **ISO 9001, 14001, 45001** certified. Analytical methods are available upon request.

PDS FEMO EU FINES REV24-01



ALL MOLYBDENUM PRODUCING SITES
OF FREEPORT-MCMORAN
ARE MOLYBDENUM MARK ASSURED
PRODUCERS



From Mine to You™ is a trademark of Climax Molybdenum Company. All rights reserved.
The trademark is currently pending registration.

www.climaxmolybdenum.com